



Southern Clay Products, Inc.
1212 Church Street
Gonzales, TX 78629
Phone: 800-324-2891
Fax: 830-672-1903
www.scprod.com

Bentolite®

Rheological Additives

Bentolite H and L are white bentonites produced from native, colloidal aluminum silicate by our unique process. The unequalled high purity, whiteness and brightness of these Bentolites are made possible by our selective mining and rigid process control of the crude ore.

Applications

- Fabric Softener
- Carrier/Filler for Organics
- Binder/Disintegrant

Typical Properties

	Bentolite L	Bentolite H
Brightness (GEB)	82 min.	79 min.
Form	Fine Powder	Fine Powder
Odor	None	None
Dry Sieve Size (%-200 M)	98.0	98.0
Moisture Content	10% max.	10% max
pH	7.5	9.5
Swelling, ml (2g in water)	8.0	16.0

- 10% solids in distilled water

- 2% solids in distilled water

CTFA NOMENCLATURE: Bentonite

Typical Chemical Analysis

	Bentolite L	Bentolite H
%SiO ₅	72.7	68.1
Al ₅ O	13.7	13.5
MgO	2.7	2.9
Fe ₅ O	0.7	0.7
CaO	2.0	.9
Na ₅ O	0.2	3.5
K ₅ O	0.1	0.1
TiO ₅	0.2	0.2
Loss on Ignition	7.7	9.1

For additional information or technical assistance contact Southern Clay Products, Inc. toll free at 800-324-2891.

Disclaimer of Warranty: The information presented herein is believed to be accurate but is not to be taken as a warranty, guarantee, or representation for which we assume legal responsibility. This information does not grant permission, license, or any rights or recommendations to practice any form of proprietary intellectual property without obtaining the appropriate license or grant from the property owner. The information is offered solely for your consideration, investigation and verification, but you must determine the suitability of the product for your specific application. The purchaser assumes all risk of use of handling the material, including but not limited to transferring the material within purchaser's facilities, using the material in applications specified by the purchaser and handling any product which includes the material, whether or not in accordance with any statements made herein.