

Incorporation:

Claytone HY easily disperses under low shear. Heat or the use of a polar activator is not required in order to obtain good dispersion. Claytone HY does not require pregelling and can be added directly with other ink ingredients into the ink batch prior to dispersion.

Use levels for Claytone HY depend upon the ink system involved and the degree of viscosity development and tack required.

For additional information or technical assistance contact Southern Clay Products, Inc. toll free at 800-324-2891.

Disclaimer of Warranty: The information presented herein is believed to be accurate but is not to be taken as a warranty, guarantee, or representation for which we assume legal responsibility. This information does not grant permission, license, or any rights or recommendations to practice any form of proprietary intellectual property without obtaining the appropriate license or grant from the property owner. The information is offered solely for your consideration, investigation and verification, but you must determine the suitability of the product for your specific application. The purchaser assumes all risk of use of handling the material, including but not limited to transferring the material within purchaser's facilities, using the material in applications specified by the purchaser and handling any product which includes the material, whether or not in accordance with any statements made herein.

